









# P1506-1 (50:50) SATURATED POLYESTER RESIN

Recommended Formulation

## **PRODUCT**

#### **Properties**

P1506-1 (50:50) is a general type saturated polyester resin, which is used together with epoxy resin (by 50:50) to produce hybrid powder coatings, giving high gloss and good flow effect.

It is also available for semi-gloss powder coatings.

#### **Specifications**

Appearance: Light yellow & clear flake

Color (DMF50%): 5-10

Acid value (mgKOH/g): 68-78

Glass Transition Temperature (°C): ≥56

Viscosity (200°C/mPa.s): 2500-4000

## Technical condition for making coatings

Extruder: SLJ-30AF

Clamp set temperature(°C): 110-120 Helix pole temperature(°C): 60 Rotational speed(rpm): 60

Powder particle size(µm .max):100

Curing condition: 180°C/15 min (metal temperature)

#### Package and Shelf Life

a. Package: net 25kgs in PE bag or multi-ply paper bag;

**b. Shelf Life:** in a ventilative,dry and clean place under 30°C, its shelf life is one year.

INGREDIENT	WEIGHT	
Polyester resin P1506-1(50:50)	300g	
Epoxy resin (E-12)	300g	
Padding	377g	
Flow agent(PV88/GLP588)	10g	
Benzoin	3g	_

10g

## Coating film properties

Leveling agent (701B)

 Film thickness(μm): 70± 10
 Gloss (60 °C) %: ≥90

 Bend (mm): ≤6
 Impact intensity(kg·cm): 50

Pencil hardness: 1H

#### Spraying methods and conditions

Oilless and rustless cold-rolled steel plate (mm): 0.5

Electrostatic spraying (kv): 50

Huangshan Jiajie New Material Technology Co.,Ltd.

Add: 13 Huangping Road, Huizhou Circular Economy Park, Huizhou District, Huangshan City, Anhui, P.R.China P.C.: 245900

TEL: 0559-3512781 3516308 3517328 FAX: 0559-3516078 3516026 3517028

E-mail: hsjiajie@vip.163.com Web: www.jiajieresin.com

Disclaimer: The information given in this sheet is based on our present research and is believed reliable, but it is solely the user's responsibility to confirm by testing for its specific use. JIAJIE MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.