

## P2606 ( 60:40 ) SATURATED POLYESTER RESIN

### PRODUCT

#### Properties

P2606 (60:40) is a saturated polyester resin, which is used together with epoxy resin (by 60:40) to produce hybrid polyester powder coatings, economical type, giving good performance properties.

#### Specifications

Appearance: Light yellow & clear flake

Color (DMF50%): 5-10

Acid value (mgKOH/g): 48-55

Glass Transition Temperature (°C): ≥55

Viscosity (200°C/mPa.s): 3000-4000

#### Technical condition for making coatings

Extruder: SLJ-30AF

Clamp set temperature(°C): 110-120

Helix pole temperature(°C): 60

Rotational speed(rpm): 60

Powder particle size(μm .max):100

Curing condition: 185°C/15 min (metal temperature)

#### Package and Shelf Life

**a. Package:** net 25kgs in PE bag or multi-ply paper bag;

**b. Shelf Life:** in a ventilative, dry and clean place under 30°C, its shelf life is one year.

#### Recommended Formulation

INGREDIENT	WEIGHT
Polyester resin P2606 (60:40)	360g
Epoxy resin (E-12)	240g
Padding	377g
Flow agent(PV88/GLP588)	10g
Benzoin	3g
Leveling agent (701B)	10g

#### Coating film properties

Film thickness(μm): 70± 10	Gloss (60°C) %: ≥90
Bend (mm): ≤6	Impact intensity(kg·cm): 50
Pencil hardness: 1H	

#### Spraying methods and conditions

Oilless and rustless cold-rolled steel plate (mm): 0.5

Electrostatic spraying (kv): 50

Huangshan Jiajie New Material Technology Co.,Ltd.

Add: 13 Huangping Road, Huizhou Circular Economy Park, Huizhou District, Huangshan City, Anhui, P.R.China P.C.: 245900

TEL: 0559-3512781 3516308 3517328  
FAX: 0559-3516078 3516026 3517028

E-mail: [hsjjajie@vip.163.com](mailto:hsjjajie@vip.163.com)  
Web: [www.jiajieresin.com](http://www.jiajieresin.com)