

P2709 (70:30) SATURATED POLYESTER RESIN

PRODUCT

Properties

P2709 (70:30) is a saturated polyester resin, which is used together with epoxy resin (by 70:30) to produce hybrid powder coatings, low temperature curing, giving excellent performance properties.

Specifications

Appearance: Light yellow & clear flake

Color (DMF50%): 5-10

Acid value (mgKOH/g): 28-32

Glass Transition Temperature (°C): ≥55

Viscosity (200°C/mPa.s): 3500-4500

Recommended Formulation

INGREDIENT	WEIGHT
Polyester resin P2709 (70:30)	420g
Epoxy resin (E-12)	180g
Padding	377g
Flow agent(PV88/GLP588)	10g
Benzoin	3g
Leveling agent (701B)	10g

Technical condition for making coatings

Extruder: SLJ-30AF

Clamp set temperature(°C): 110-120

Helix pole temperature(°C): 70

Rotational speed(rpm): 60

Powder particle size(μm .max): 100

Curing condition: 160°C/15min (metal temperature)

Coating film properties

Film thickness(μm): 70± 10 Gloss (60°C) %: ≥90

Bend (mm): ≤6 Impact intensity(kg·cm): 50

Pencil hardness: 1H

Package and Shelf Life

a. Package: net 25kgs in PE bag or multi-ply paper bag;

b. Shelf Life: in a ventilative, dry and clean place under 30°C, its shelf life is one year.

Spraying methods and conditions

Oilless and rustless cold-rolled steel plate (mm): 0.5

Electrostatic spraying (kv): 50

Huangshan Jiajie New Material Technology Co.,Ltd.

Add: 13 Huangping Road, Huizhou Circular Economy Park, Huizhou District, Huangshan City, Anhui, P.R.China
P.C.: 245900

TEL: 0559-3512781 3516308 3517328
FAX: 0559-3516078 3516026 3517028

E-mail: hsjjjie@vip.163.com
Web: www.jiajieresin.com