



## P3907(93:7) SATURATED POLYESTER RESIN

## PRODUCT

Properties	Recommended Formulation		
P3907(93:7) is a saturated polyester resin, which is used	INGREDIENT	WEIGHT	
together with TGIC (by 93:7) to produce pure polyester powder coatings, general type, giving good flow effect and wonderful mechanical properties	Polyester resin P3907(93:7)	600g	
	TGIC	45g	
	TiO2 (R902)	342g	
)	Flow agent(PV88/GLP588)	10g	
Specifications	Benzoin	3g	
ppearance: Light yellow & clear flake			
olor (DMF50%): 5-10			
cid value (mgKOH/g): 30-35			
ass Transition Temperature (°C): ≥65			
т. н. (200° с.). (200 с.).			
/iscosity (200°C/mPa.s): 4000-5000			
echnical condition for making coatings	Coating film properties		
xtruder: SLJ-30AF		<u>Gloss (60°C) %: ≥90</u>	
amp set temperature(°C): 110-120	<u>Bend (mm): ≤6</u>	mpact intensity(kg·cm): 50	
elix pole temperature(°C): 60 otational speed(rpm): 60	Pencil hardness: 1H		
owder particle size(µm .max):100			
uring condition: 200°C/10 min (metal temperature)			
Package and Shelf Life	Spraying methods and condition	Spraying methods and conditions	
• Package: net 25kgs in PE bag or multi-ply paper bag;	Oilless and rustless cold-rolled ste	Oilless and rustless cold-rolled steel plate (mm): 0.5	
<b>D. Shelf Life:</b> in a ventilative,dry and clean place under 30°C, its shelf life is one year	Electrostatic spraying (kv): 50		

Huangshan Jiajie New Material Technology Co.,Ltd.

Add: 13 Huangping Road,Huizhou Circular Economy Park,Huizhou District, Huangshan City,Anhui, P.R.China P.C.: 245900

30°C, its shelf life is one year.

TEL: 0559-3512781 3516308 3517328 FAX: 0559-3516078 3516026 3517028 E-mail: hsjiajie@vip.163.com Web: www.jiajieresin.com

Disclaimer: The information given in this sheet is based on our present research and is believed reliable, but it is solely the user's responsibility to confirm by testing for its specific use.JIAJIE MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.