

## P3916( 93:7 ) SATURATED POLYESTER RESIN

### PRODUCT

#### Properties

P3916(93:7) is a saturated polyester resin, which is used together with TGIC (by 93:7) to produce pure polyester powder coatings, Tin-free, giving high gloss, excellent flow effect.

#### Specifications

Appearance: Light yellow & clear flake

Color (DMF50%): 5-10

Acid value (mgKOH/g): 30-36

Glass Transition Temperature (°C): ≥65

Viscosity (200°C/mPa.s): 4600-5600

#### Technical condition for making coatings

Extruder: SLJ-30AF

Clamp set temperature(°C): 110-120

Helix pole temperature(°C): 60

Rotational speed(rpm): 60

Powder particle size(μm .max): 100

Curing condition: 200°C/10 min (metal temperature)

#### Package and Shelf Life

**a. Package:** net 25kgs in PE bag or multi-ply paper bag;

**b. Shelf Life:** in a ventilative, dry and clean place under 30°C, its shelf life is one year.

#### Recommended Formulation

INGREDIENT	WEIGHT
Polyester resin P3916(93:7)	600g
TGIC	45g
TiO <sub>2</sub> (R902)	342g
Flow agent(PV88/GLP588)	10g
Benzoin	3g

#### Coating film properties

Film thickness(μm): 70± 10      Gloss (60°C) %: ≥90  
 Bend (mm): ≤6      Impact intensity(kg·cm): 50  
 Pencil hardness: 1H

#### Spraying methods and conditions

Oilless and rustless cold-rolled steel plate (mm): 0.5

Electrostatic spraying (kv): 50

Huangshan Jiajie New Material Technology Co.,Ltd.

Add: 13 Huangping Road, Huizhou Circular Economy Park, Huizhou District, Huangshan City, Anhui, P.R.China  
 P.C.: 245900

TEL: 0559-3512781 3516308 3517328  
 FAX: 0559-3516078 3516026 3517028

E-mail: hsjjiajie@vip.163.com  
 Web: www.jiajieresin.com